

TECHNICAL DATA SHEET



CPP 0630 BASECOAT READY MIXED COLOURS

DESCRIPTION

BASECOAT READY MIXED COLOURS are suitable for air-drying or oven-baking. They have excellent covering power, and easy application qualities. They are quick drying and have good chemical resistance. They may be used for small repairs or complete surface recoating.

MIXING

Mix by volume 2 parts of BASECOAT READY MIX COLOUR : 1 part BASECOAT THINNER. Additional Basecoat Thinner may be added if required, however this may reduce the opacity. Stir well and filter before use.

SPRAY PRESSURE

50-60 PSI (3-4 bar) at gun.

GUN SET-UP

1.4-1.6 Compliant spray gun.

APPLICATION

Apply 2-3 coats with 5-10 minutes between coats to allow to flash off. The basecoat must be over coated with 2K clear coat within 1 hour of application to ensure inter-coat adhesion.

POT LIFE

Approximately 24hrs at 20°C.

DRYING

Touch Dry: 20 minutes.



TECHNICAL DATA SHEET

CPP 0630 BASECOAT READY MIXED COLOURS

FLASH POINT

22°C - 32°C.

STORAGE

12 months in original sealed containers.

HEALTH & SAFETY

Please refer to relevant Health and Safety Data Sheet, reference no. HSD 0630.

NOTE

This data relates only to the product designated herein and does not apply to use in combination with any other materials or in any other process.

The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

Our product range is under continuous development and therefore products and specifications are subject to change without notice.

This product is for professional use only.

All trademarks, registered trademarks, brands and product names respected.